

CHAPAS LAMINADO EN FRÍO Y CALIENTE

TABLA DE PESOS TEÓRICOS

		LAMINADOS EN FRIO							
Espesor		1,000	1,220	1,220	1,500	1,025	1,245	1,245	1,500
		x	x	x	x	x	x	x	x
B.W.G.	mm.	2,000	2,440	3,000	3,000	2,000	2,440	3,000	3,000
29	0.30	4.71							
28	0.35	5.50							
27	0.40	6.28	9.35	11.49	14.13				
26	0.45	7.07	10.52	12.93	15.90				
25	0.50	7.85	11.68	14.37	17.66				
24	0.55	8.64	12.85	15.80	19.43				
	0.60	9.42	14.02	17.24	21.20				
23	0.65	10.21	15.19	18.68	22.96				
22	0.70	10.99	16.36	20.11	24.73				
21	0.80	12.56	18.69	22.98	28.26				
20	0.90	14.13	21.03	25.86	31.79				
	1.00	15.70	23.37	28.73	35.33				
19	1.10	17.27	25.70	31.60	38.86				
18	1.25	19.63	29.21	35.91	44.16				
17	1.50	23.55	35.05	43.10	52.99				
16	1.60	25.12	37.39	45.97	56.52	25.75			
15	1.80	28.26	42.06	51.72	63.59	28.97			
14	2.00	31.40	46.74	57.46	70.65	32.19	47.69	58.64	
13	2.25	35.33	52.58	64.64	79.48	36.21	53.66	65.97	
12	2.50	39.25	58.42	71.83	88.31	40.23	59.62	73.30	

